

TECHNICAL CHARACTERISTICS

PURLINE | wineo 1000 to glue

Permanently elastic polyurethane flooring according to EN 16776
Without the addition of chlorin, without plasticisers or solvents.

wineo

	wood L	wood XL	stone L
Format	1298 x 199 mm	1500 x 250 mm	645 x 335 mm
Product thickness	2.2 mm	2.2 mm	2.2 mm
Weight	3.0 kg/m ²	3.0 kg/m ²	3.0 kg/m ²
Planks / m² per box	20 / 5.17 m ²	14 / 5.25 m ²	22 / 4.75 m ²
Boxes / m² per pallet	60 / 310.20 m ²	56 / 294 m ²	66 / 313.50 m ²



Guarantee You can find our guarantee conditions at – www.wineo.de

Classification			Product composition	
	Utilization class 23 EN ISO 10874	Domestic area with intensive usage	1	Top element • PU-top layer with surface structure • decor paper • stabilisation
	Utilization class 32 EN ISO 10874	Commercial sector with average usage		
	Scratch resistance EN 16776, annex A	Utilization class 23: > 3 N Utilization class 32: > 5 N		
	R9 Anti slip category DIN 51130	R 9	2	Base layer ecuran high performance composite material
	Staining and chemical resistance EN ISO 26987	Very good resistance according to the concentration and residence time		
	Light fastness EN ISO 105-B02	~ 7	3	Backing Integrated Fleece TEC System
	Residual indentation EN ISO 24343-1	≤ 0.10 mm	  www.blauer-engel.de/uz120  	
	Effect of a furniture leg EN 424	Utilization class 23: Foot type 3 Utilization class 32: Foot type 2 no visible change		
	Castor chair test EN 425	25000 revolutions no damage with rolls type W		
	Thermal resistance ISO 8302	0.01 (m²K)/W		
	Impact sound reduction EN ISO 10140	~ 8 dB ~ 17 dB in the system with silentPLUS		
	Dimension stability EN ISO 23999	≤ 0.15 %		
	Flexural behaviour EN ISO 24344	≥ 20 mm		
	REACH	free from SVHC substances ≥ 0.1 %		
	Disposal	<u>Private:</u> possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		

Relevant Information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperatur of 29 °C.
- Cleaning and care: See separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.